

TECHNICAL DATA SHEET

DUBL-CHEK RED POWDER No. 6

RED MAGNETIC DUSTING POWDER

Description: DUBL-CHEK Red Powder No. 6 is a highly refined non-fluorescent red magnetic powder used for dry method magnetic particle inspection. It is designed to be used in visible light to reveal discontinuities. The particles respond to magnetic leakage fields created by discontinuities in ferromagnetic material. Particles rapidly collect at leakage fields producing red indications.

Properties

Particle Colour:	Red
Specific Gravity:	2.5 – 3.0 g/ml
Particle Size:	15 – 160 µm (average 75µm)
Sensitivity:	8 lines on an AISI Ketos tool steel ring
Temperature limit:	315°C

Packaging

4.5kg	Product Code: 1536/10LBS
22.5kg	Product Code: 1536/50LBS

Storage /Shelf Life

Keep away from moisture and sunlight.
Keep the container closed when not in use.
Shelf life: 36 months (3 years) from date of manufacture.
Refer to NDT Shelf Life and Storage Recommendations for further information.

Specifications

Particles meet or exceed industry specifications including;
ASTM E-1444, MIL-STD-1949, AMS 3040, MIL-STD-271, NAVSEA 250-1500-1, NTR-1E

Batch Numbers

Batch numbers can be found on the bottom of aerosol cans or labels of bulk containers. Certificate of Conformance documents are provided with the product or can be downloaded from www.callington.com

Special Features

Particles are easily agitated, fast acting and produce defined indications
Particles meet specification requirements
Can be used with both stationary and portable magnetic test equipment
Can be used at elevated temperatures
The red colour gives a clear contrasting colour to backgrounds.

TECHNICAL DATA SHEET

Instructions

Note: These instructions describe the basic process, but they may need to be amended by the user to comply with applicable specifications and/or inspection criteria provided by the contracting agency.

1. Clean the test surface and allow it to dry.
2. Apply **Red Powder No. 6** to the part with a powder spray bulb or powder blower.
3. Magnetise the area to be inspected.
4. As the current is being applied, dust the powder over the part. If excessive powder is visible, gently blow the extra powder off.
5. Inspect the surface under visible light.
6. Collections of particles will reveal discontinuities at the leakage fields.
7. Clean and repeat the process; changing the orientation of the magnetising direction.

Health & Safety

Consult the MSDS for Safety and Health information.

Get medical attention if irritation develops and persists. Ensure that medical personnel are aware of the material(s) involved, and take precautions to protect themselves.

WARRANTY – All statements, information and data presented herein are believed to be accuracy and reliable but are not to be taken as a guarantee, expressed or implied, for which seller assumes legal responsibility and they are offered solely for your consideration, investigation and verification. Statements or suggestions concerning possible use of this product are made without representation or warranty that any such use is free of patent infringement and are not recommendations to infringe on any patent.
22 August 2007
